

## TESTLINER TLK QUALITY SPECIFICATION

	Properties	Units	Standard							Method of testing
1	Grammage	g/m <sup>2</sup>	120	125	135	140	150	160	170	ISO 536
2	Bursting strength	kPa	335	350	380	390	420	440	450	ISO 2759
3	Compressive strength – short span test (SCT MD)	kN/m	2,7	2,8	3,0	3,1	3,3	3,5,	3,75	ISO 9895
4	Water absorbency mean value top and back layers (Cobb <sub>60</sub> )	g/m <sup>2</sup>	70							ISO 535
5	Moisture	%	7,0							ISO 287

	Properties	Units	Standard	Method of testing
1	Grammage	g/m <sup>2</sup>	± 3%	ISO 536
2	Moisture	%	±1,0	ISO 287

All specifications are at ISO 187 standard conditions of (50±2) % and (23±1)°C.  
The samples for testing average quality are selected according ISO 186 standard.